cited in the European Search Report of EP03 77 2791.4 Your Ref.: NSC-17924-LAP Patent Abstracts of Japan

EUROPEAN PATENT OFFICE

PUBLICATION NUMBER

02047240

PUBLICATION DATE

16-02-90

APPLICATION DATE

10-08-88

APPLICATION NUMBER

63197854

APPLICANT: NIPPON STEEL CORP;

INVENTOR: OCHITATSURO;

INT.CL.

C22C 38/14 C22C 38/00

TITLE

MEDIUM CARBON TOUGH AND HARD STEEL

ABSTRACT:

PURPOSE: To ensure strength and toughness equal to or higher than those of the conventional tempered material in an as-hot-forged state, e.g., by specifying respective contents of oxide-forming elements, such as Ti and Zr, in a medium carbon steel and incorporating the grains of oxide and composite body of oxide and MnS having a specific grain size.

CONSTITUTION: A medium carbon tough and hard steel has a composition consisting of, by weight ratio, 0.10-0.60% C, 0.01-3.00% Si, 0.20-3.00% Mn, 0.01-0.30% S, 0.03.0.30% V, 0.005-0.060% N, further one or more kinds among 0.001-0.100% Ti, 0.001-0.100% Zr, 0.001-0.200% Hf, 0.001-0.150% Y, 0.001-0.150% La, 0.001-0.150% Ce, 0.001-0.050% Ca, and 0.001-0.010% Mg, and the balance Fe with inevitable impurities. Further, the grains of oxide and composite body of oxide and MnS of 0.1-l0um grain size are incorporated by 1×10³ to 1×10⁶ pieces/mm³.

Moreover, the contents of Al and P are limited to ≤0.005% and ≥0.03%, respectively. By this method, a steel having superior strength and toughness in an as-hot-forged state can be obtained while obviating the necessity of tempering treatment.

COPYRIGHT: (C)1990, JPO& Japio